



### **CHARACTERISTICS**

- -Chrome matte finish
- -Water-repellent
- Anti-yellowing
- Anti-contamination

### **APPLICATIONS**

For automotive use (other uses may apply).

### **APPLICATION AREAS**

Flat surfaces, simple curves, and compound curves

# **APPLICATION METHOD**

Paint protection films are to be professionally installed by trained, authorized installers.

# **SHELF LIFE**

Paint protection films should be installed within one year from the date of purchase.

# LAYER DESCRIPTIONS

### Top Coat (Matte)

Provides matte finish

### TPU

High-clarity and impact-resistant

### Pattern + TPU

Provides Chrome finish

# Pressure-Sensitive Adhesive (PSA)

For easy installation

### **Release Liner**

Protects film before use

### LAYER THICKNESS

 $225 \pm 10 \mu m$ 

# STEK® Paint Protection Film Technical Data Sheet

### **PRODUCT IMAGE**




### STORAGE INSTRUCTIONS

Recommended Temperature Range: 20±2 °C (68±2 °F) Recommended Relative Humidity: 40-60%

Avoid extreme temperature ranges in storage. Store the product in its original packaging in a horizontal orientation, away from direct sunlight. Do not place heavy objects on top of the packaging, as this may damage the product.

# **STRUCTURE**



# **PROPERTIES**

Gloss	>50 Gu	ASTM D523
Coating Layer Crack	>45 mm	ASTM D412
Adhesion (30 min.)	>1400	ASTM D3330
Adhesion (24 hrs)	>2000	
Self-Healing	Standard	
Hydrophobicity	Water-repellent	
Weathering	No change 6500 W Xenon Arc Irradiance: 0.51 W/m² (340 nm), 65° C Humidity: 50%, R.H. 1000 hrs	



### **PACKAGE DIMENSIONS**

**Box size** 

1630 x 185 x 180 (mm)

# **Technical Data Sheet**

# **ROLL CONFIGURATIONS**

60 In. x 59 ft

(1524 mm x 18m)

### **NOTES**

All data have been collected by STEK Automotive through internal testing standards and methods. Results may differ when using other testing standards.

Reported values are expected properties and should not be used for product certification.

The provided technical information consists of representative product data and should not be used for specification purposes. Unless otherwise noted, all tests are performed at room temperature.

All concerns regarding warranty and liability are subject to the terms and conditions of sale. When applicable, these terms and conditions are governed by prevailing laws.

Prior to application, the user must determine the suitability of the product for its intended use, and assumes all risk and liability therein.

# WARRANTY

12-year warranty

Only applicable in the case of proper handling and use. Terms and conditions apply.